



CALCINED ALUMINA

F50

Analytical Results

Property	Unit	Specifications	TC Value
Al_2O_3	%	99.4 (min) 99.6 (Typical)	99.5
Fe_2O_3	%	0.03 (max) 0.02 (Typical)	0.015
LOI	%	0.3 (max) 0.12 (Typical)	0.12
D50 (Malv)	Micron	55 (max) 50 (Typical)	52
$Na_2O(T)$	%	0.45 (max) 0.3 (Typical)	0.34
SiO_2	%	0.03 (max) 0.02 (Typical)	0.006
SSA	m ² /g	2 (max) 0.62 (Typical)	0.59